

AEROSPACE MATERIAL SPECIFICATION



AMS3631

REV. D

Issued	1957-01
Revised	1998-12
Stabilized	2011-11
Superseding AMS3631C	

Polyvinyl Chloride (PVC) Plastic Extrusions
High Temperature, Flexible

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "Stabilized" by SAE AMS P, Polymeric Materials Committee, and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of AMS3631D

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3631D>**

1. SCOPE:

1.1 Form:

This specification covers a polyvinyl chloride (PVC) plastic in the form of extruded tubing, cord, tape, and shapes.

1.2 Application:

These extrusions have been used typically as sleeving on wire or as bus bar insulation, particularly where transparency of the sleeve is desired, for operating temperatures up to 120 °C (248 °F), but usage is not limited to such applications. Each application should be considered individually.

1.3 Safety-Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAENORM.COM : Click to view the full PDF of AMS3631D

2.1 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

- ASTM D 149 Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies
- ASTM D 471 Rubber Property - Effect of Liquids
- ASTM D 570 Water Absorption of Plastics
- ASTM D 573 Rubber - Deterioration in an Air Oven
- ASTM D 746 Brittleness Temperature of Plastics and Elastomers by Impact
- ASTM D 876 Nonrigid Vinyl Chloride Polymer Tubing Used for Electrical Insulation
- ASTM G 21 Determining Resistance of Synthetic Polymeric Materials to Fungi

3. TECHNICAL REQUIREMENTS:

3.1 Material:

Shall be polyvinyl chloride (PVC) or one of its co-polymers and shall contain no mercury compounds.

3.1.1 Color: Colorless and transparent. Colored transparent, translucent, or opaque material shall be furnished only when specified.

3.1.2 Material shall be considered colorless if the color identification of the wire inside the tubing is legible and shall be considered transparent if other identification marking on the wire inside the tube is legible.

3.2 Properties:

Extrusions shall conform to the requirements shown in Table 1, 3.2.10, and 3.2.11; tests shall be performed on the extrusions supplied and in accordance with specified test methods, insofar as practicable.

TABLE 1- Properties

	Property	Requirement	Test Method
3.2.1	Tensile Strength, min	1800 psi (12.4 MPa)	ASTM D 876
3.2.2	Elongation, min	250%	ASTM D 876
3.2.3	Water Absorption (24 hours immersion), change in weight, max	1.5%	ASTM D 570
3.2.4	Flammability, time to cease burning, max (See 8.2)	15 seconds	4.5.1
3.2.5	Dielectric Strength (short time test)		ASTM D 876 (tubing) ASTM D 149 (other forms)
	Under 0.020 inch (0.51 mm) thick, min	750 volts per mil (29.5 kV/mm)	
	0.020 inch (0.51 mm) thick and over, min	15,000 volts per mil (591 kV/mm)	
3.2.6	Fungus Resistance	Rating of 1 or less	ASTM G 21
3.2.7	Oil Resistance	IRM 903 (See 8.3)	ASTM D 471 100 °C ± 1 (212 °F ± 2) 8 hours ± 0.25 4.5.2
3.2.7.1	Shrinkage, Lengthwise, max	10%	
3.2.7.2	Bend, 180 degrees around a 0.25 inch (6.4 mm) diameter at approximately 60 degrees per second at room temperature.	No cracking	
3.2.7.3	Decomposition	None	
3.2.7.4	Surface Tackiness	None	
3.2.8	Dry Heat Resistance		ASTM D 573 130 °C ± 1 (266 °F ± 2) 2 hours ± 0.25 4.5.2
3.2.8.1	Shrinkage, Lengthwise, max	10%	
3.2.8.2	Surface Tackiness	None	
3.2.8.3	Loss of Transparency	Negligible	

TABLE 1- Properties

	Property	Requirement	Test Method
3.2.9	Low-Temperature Brittleness At -32 °C ± 1 (-26 °F ± 2) as received	Pass	4.5.3

3.2.10 Weather Resistance: When specified, extrusions shall have weather resistance acceptable to purchaser, determined by a procedure agreed upon by purchaser and supplier.

3.2.11 Corrosion: Extrusions shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service, determined by a procedure agreed upon by purchaser and supplier. Discoloration of metal shall not be considered objectionable.

3.3 Quality:

Extrusions, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign material as commercially practicable, and free from internal imperfections detrimental to usage of the product.

3.4 Sizes and Tolerances:

3.4.1 Tubing: Shall conform to Table 2; for intermediate nominal ID, use the tolerance for the next larger size.

TABLE 2A - ID and Wall Thickness Tolerances, Inch/Pound Units

Nominal ID Inches	ID, Inches minimum	ID, Inches maximum	Nominal Wall Thickness Inch	Wall Thickness Tolerance, Inch Plus and Minus
0.022	0.020	0.027	0.012	0.002
0.027	0.025	0.032	0.012	0.002
0.034	0.032	0.039	0.016	0.003
0.042	0.040	0.049	0.016	0.003
0.053	0.051	0.061	0.016	0.003
0.066	0.064	0.072	0.016	0.003
0.085	0.081	0.089	0.016	0.003
0.095	0.091	0.101	0.016	0.003
0.106	0.102	0.112	0.016	0.003
0.118	0.114	0.124	0.020	0.003
0.133	0.129	0.141	0.020	0.003
0.148	0.144	0.158	0.020	0.003
0.166	0.162	0.178	0.020	0.003

TABLE 2A - ID and Wall Thickness Tolerances, Inch/Pound Units (Continued)

Nominal ID Inches	ID, Inches minimum	ID, Inches maximum	Nominal Wall Thickness Inch	Wall Thickness Tolerance, Inch Plus and Minus
0.186	0.182	0.198	0.020	0.003
0.208	0.204	0.224	0.020	0.003
0.234	0.229	0.249	0.020	0.003
0.263	0.258	0.278	0.020	0.003
0.294	0.289	0.311	0.020	0.003
0.330	0.325	0.347	0.020	0.003
0.312	0.312	0.334	0.025	0.003
0.375	0.375	0.399	0.025	0.003
0.437	0.438	0.462	0.025	0.003
0.500	0.500	0.524	0.025	0.003
0.625	0.625	0.655	0.030	0.003
0.750	0.750	0.786	0.035	0.005
0.875	0.875	0.911	0.035	0.005
1	1.000	1.036	0.035	0.005
1.125	1.250	1.290	0.040	0.005
1.500	1.500	1.550	0.045	0.006
1.750	1.750	1.812	0.055	0.008
2	2.000	2.070	0.060	0.010
2.125	2.250	2.330	0.065	0.010
2.500	2.500	2.590	0.070	0.010

TABLE 2B - ID and Wall Thickness Tolerances, SI Units

Nominal ID Millimeters	ID Millimeters minimum	ID Millimeters maximum	Nominal Wall Thickness Millimeters	Wall Thickness Tolerance Millimeter plus and minus
0.56	0.51	0.69	0.30	0.05
0.69	0.64	0.81	0.30	0.05
0.86	0.81	0.99	0.41	0.08
1.07	1.02	1.24	0.41	0.08
1.35	1.30	1.55	0.41	0.08
1.68	1.63	1.83	0.41	0.08
2.16	2.06	2.26	0.41	0.08
2.41	2.31	2.57	0.41	0.08
2.69	2.59	2.84	0.41	0.08

TABLE 2B - ID and Wall Thickness Tolerances, SI Units (Continued)

Nominal ID Millimeters	ID Millimeters minimum	ID Millimeters maximum	Nominal Wall Thickness Millimeters	Wall Thickness Tolerance Millimeter plus and minus
3.00	2.90	3.15	0.51	0.08
3.38	3.28	3.58	0.51	0.08
3.76	3.66	4.01	0.51	0.08
4.22	4.11	4.52	0.51	0.08
4.72	4.62	5.03	0.51	0.08
5.28	5.18	5.69	0.51	0.08
5.94	5.82	6.32	0.51	0.08
6.68	6.55	7.06	0.51	0.08
7.47	7.34	7.90	0.51	0.08
8.38	8.26	8.81	0.51	0.08
7.94	7.92	8.48	0.64	0.08
9.52	9.52	10.13	0.64	0.08
11.11	11.12	11.73	0.64	0.08
12.70	12.70	13.31	0.64	0.08
15.88	15.88	16.64	0.76	0.08
19.05	19.05	19.96	0.89	0.13
22.22	22.22	23.14	0.89	0.13
25.40	25.40	26.31	0.89	0.13
31.75	31.75	32.77	1.02	0.13
38.10	38.10	39.37	1.14	0.15
44.45	44.45	46.02	1.40	0.20
50.80	50.80	52.58	1.52	0.25
57.15	57.15	59.18	1.65	0.25
63.50	63.50	65.79	1.78	0.25

3.4.2 Tape: Shall conform to Table 3 and 4.

3.4.2.1 Width:

TABLE 3A - Tape Width Tolerances, Inch/Pound Units

Nominal Width Inches	Tolerance, Inch Plus and Minus
Up to 0.500, incl	0.016
Over 0.500 to 0.625, incl	0.020

TABLE 3A - Tape Width Tolerances, Inch/Pound Units

Nominal Width Inches	Tolerance, Inch Plus and Minus
Over 0.625 to 0.750, incl	0.025
Over 0.750 to 1.000, incl	0.032
Over 1.000 to 1.250, incl	0.040
Over 1.250 to 2.000, incl	0.064

TABLE 3B - Tape Width Tolerances, SI Units

Nominal Width Millimeters	Tolerance, Millimeters Plus and Minus
Up to 12.70, incl	0.41
Over 12.70 to 15.88, incl	0.51
Over 15.88 to 19.05, incl	0.64
Over 19.05 to 25.40, incl	0.81
Over 25.40 to 31.75, incl	1.02
Over 31.75 to 50.80, incl	1.63

3.4.2.2 Thickness:

TABLE 4A - Tape Thickness Tolerances, Inch/Pound Units

Nominal Thickness Inch	Tolerance, Inch Plus and Minus
Up to 0.019, incl	0.005
Over 0.019 to 0.031, incl	0.008
Over 0.031	0.010

TABLE 4B - Tape Thickness Tolerances, SI Units

Nominal Thickness Millimeter	Tolerance, Millimeter Plus and Minus
Up to 0.48, incl	0.13
Over 0.48 to 0.79, incl	0.20
Over 0.79	0.25

3.4.3 Cord: Shall conform to Table 5:

TABLE 5A - Cord Tolerances, Inch/Pound Units

Nominal Dimension Inch	Tolerance, Inch Plus and Minus
Up to 0.156, incl	0.005
Over 0.156 to 0.188, incl	0.008
Over 0.188	0.010

TABLE 5B - Cord Tolerances, SI Units

Nominal Dimension Millimeters	Tolerance, Millimeter Plus and Minus
Up to 3.96, incl	0.13
Over 3.96 to 4.78, incl	0.20
Over 4.78	0.25

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The manufacturer shall supply all samples and shall be responsible for performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conform to the specified requirements.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Tensile strength (3.2.1), elongation (3.2.2), dielectric strength (3.2.5), loss of transparency (3.2.8.3), and tolerances (3.4) are acceptance tests and shall be performed on each lot.
- 4.2.2 Preproduction Tests: All technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of extrusions to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.1, and when purchaser deems confirmatory testing to be required.