

NOTICE OF
ADOPTION

ADOPTION NOTICE
20 December 1991
AMS 6305B
1 January 1991
SUPERSEDING
AMS 6305A
1 August 1986

AMS 6305B was adopted on 20 December 1991 and is approved for use by the Department of Defense (DOD). Copies of this document are stocked at the Standardization Documents Order Desk, Bldg 4D, 700 Robbins Avenue, Philadelphia, Pennsylvania 19111-5094 for issue to DOD activities only. Other Government Agencies, contractors, private concerns, or other requestors must obtain the document from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

Title of Document: Steel Bars, forgings, and Tubing,
Low-Alloy, Heat Resistant
0.95Cr - 0.55Mo - 0.30V (0.40 - 0.50C)
Vacuum Arc Melted

Date of Specific Issue Adopted: 1 January 1991

Releasing Non-Government Standards Body: SAE

Custodians:

Air Force - 11
Army - MR
Navy - AS

Military Coordinating Activity
Air Force - 11
(Project No: 9510-0824)

FSC 9510

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.



400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE AMS-6305

REV
BIssued 1973-05-15
Revised 1991-01-01

Superseding AMS-6305A

Submitted for recognition as an American National Standard

STEEL BARS, FORGINGS, AND TUBING, LOW-ALLOY, HEAT-RESISTANT

0.95Cr - 0.55Mo - 0.30V (0.40 - 0.50C)

Vacuum Arc Remelted

UNS K14675

1. SCOPE:

1.1 Form: This specification covers a premium aircraft-quality, low-alloy, heat-resistant steel in the form of bars, forgings, mechanical tubing, and stock for forging or heading.

1.2 Application: Primarily for parts, such as compressor discs, turbine discs, shafts, and fasteners, for use in service up to 1000°F (538°C) and subject to very rigid inspection standards.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

2.1.1 Aerospace Material Specifications:

AMS-2251 - Tolerances, Low-Alloy Steel Bars
 MAM-2251 - Tolerances, Metric, Low-Alloy Steel Bars
 AMS-2253 - Tolerances, Carbon and Alloy Steel Tubing
 MAM-2253 - Tolerances, Metric, Carbon and Alloy Steel Tubing
 AMS-2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
 AMS-2300 - Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
 MAM-2300 - Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure, Metric (SI) Measurement
 AMS-2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except forgings and Forging Stock

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

SAE AMS-6305 Revision B

2.1.1 (Continued):

AMS-2372 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, forgings and Forging Stock
 AMS-2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
 AMS-2808 - Identification, forgings

2.1.2 Aerospace Standards:

AS1182 - Standard Machining Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing

2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM A 370 - Mechanical Testing of Steel Products
 ASTM A 604 - Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets
 ASTM E 112 - Determining Average Grain Size
 ASTM E 350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

2.3 U.S. Government Publications: Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

| | min | max |
|------------|------|----------------|
| Carbon | 0.40 | 0.50 |
| Manganese | 0.40 | 0.70 |
| Silicon | 0.15 | 0.35 |
| Phosphorus | -- | 0.015 |
| Sulfur | -- | 0.015 |
| Chromium | 0.80 | 1.10 |
| Molybdenum | 0.45 | 0.65 |
| Vanadium | 0.25 | 0.35 |
| Nickel | -- | 0.25 |
| Copper | -- | 0.35 |
| Lead | -- | 0.001 (10 ppm) |

SAE AMS-6305 Revision B

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS-2259.

3.2 Condition: The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A 370:

3.2.1 Bars:

3.2.1.1 Bars 0.500 Inch (12.70 mm) and Under in Nominal Diameter or Distance Ø Between Parallel Sides: Cold finished having tensile strength not higher than 125,000 psi (862 MPa) or hardness not higher than 27 HRC.

3.2.1.2 Bars Over 0.500 Inch (12.70 mm) in Nominal Diameter or Distance Between Parallel Sides: Hot finished and annealed having hardness not higher than 229 HB, or equivalent, except that bars ordered cold finished may have hardness as high as 248 HB, or equivalent.

3.2.2 Forgings: Annealed having hardness not higher than 248 HB, or equivalent.

3.2.3 Mechanical Tubing: Cold finished having hardness not higher than 25 HRC, or equivalent, except that tubing ordered hot finished and annealed shall have hardness not higher than 99 HRB, or equivalent.

3.2.4 Stock for Forging or Heading: As ordered by the forging or heading manufacturer.

3.3 Properties: The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A 370:

3.3.1 Macrostructure: Visual examination of transverse sections as in 4.3.3 Ø from bars, billets, tube rounds or tubes, and stock for forging or heading, etched in accordance with ASTM A 604 in hot hydrochloric acid, shall show no pipe or cracks. Except as specified in 3.3.1.1, porosity, segregation, inclusions, and other imperfections for product 36 square inches (232 cm^2) and under in nominal cross-sectional area shall be no worse than the following macrographs of ASTM A 604; macrostructure standards for product over 36 square inches (232 cm^2) in nominal cross-sectional area shall be as agreed upon by purchaser and vendor:

| Class | Condition | Severity |
|-------|--------------------|----------|
| 1 | Freckles | A |
| 2 | White Spots | A |
| 3 | Radial Segregation | B |
| 4 | Ring Pattern | B |

3.3.1.1 If tubes are produced directly from ingots or large blooms, transverse sections may be taken from tubes rather than tube rounds. Macrostructure standards for such tubes shall be as agreed upon by purchaser and vendor.

SAE AMS-6305 Revision B

3.3.2 Grain Size: Predominantly 5 or finer with occasional grains as large as 3 permissible, determined in accordance with ASTM E 112.

3.3.3 Decarburization:

3.3.3.1 Bars and tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.

3.3.3.2 Allowable decarburization of bars, billets, and tube rounds ordered for redrawing or forging or to specified microstructural requirements shall be as agreed upon by purchaser and vendor.

3.3.3.3 Decarburization of bars to which 3.3.3.1 or 3.3.3.2 is not applicable shall be no greater than shown in Table I:

TABLE I

| Nominal Diameter or Distance Between Parallel Sides Inches | Depth of Decarburization Inch |
|------------------------------------------------------------------|-------------------------------------|
| Up to 0.375, incl | 0.015 |
| Over 0.375 to 0.500, incl | 0.017 |
| Over 0.500 to 0.625, incl | 0.019 |
| Over 0.625 to 1.000, incl | 0.022 |
| Over 1.000 to 1.500, incl | 0.025 |
| Over 1.500 to 2.000, incl | 0.030 |
| Over 2.000 to 2.500, incl | 0.035 |
| Over 2.500 to 3.000, incl | 0.040 |
| Over 3.000 to 4.000, incl | 0.045 |

TABLE I (SI)

| Nominal Diameter or Distance Between Parallel Sides Millimetres | Depth of Decarburization Millimetres |
|-----------------------------------------------------------------------|--------------------------------------------|
| Up to 9.52, incl | 0.38 |
| Over 9.52 to 12.70, incl | 0.43 |
| Over 12.70 to 15.88, incl | 0.48 |
| Over 15.88 to 25.40, incl | 0.56 |
| Over 25.40 to 38.10, incl | 0.64 |
| Over 38.10 to 50.80, incl | 0.76 |
| Over 50.80 to 63.50, incl | 0.89 |
| Over 63.50 to 76.20, incl | 1.02 |
| Over 76.20 to 101.60, incl | 1.14 |

3.3.3.3.1 Limits for depth of decarburization of bars over 4.000 inches (101.60 mm) in nominal diameter or distance between parallel sides shall be as agreed upon by purchaser and vendor.

SAE AMS-6305 Revision B

3.3.3.4 Decarburization of tubing to which 3.3.3.1 or 3.3.3.2 is not applicable shall be no greater than shown in Table II:

TABLE II

| Nominal Wall Thickness Inches | Depth of Decarburization | |
|----------------------------------|--------------------------|-------|
| | ID | OD |
| Up to 0.109, incl | 0.008 | 0.020 |
| Over 0.109 to 0.203, incl | 0.010 | 0.025 |
| Over 0.203 to 0.400, incl | 0.012 | 0.030 |
| Over 0.400 to 0.600, incl | 0.015 | 0.035 |
| Over 0.600 to 1.000, incl | 0.017 | 0.040 |
| Over 1.000 | 0.020 | 0.045 |

TABLE II (SI)

| Nominal Wall Thickness Millimetres | Depth of Decarburization | |
|---------------------------------------|--------------------------|------|
| | ID | OD |
| Up to 2.77, incl | 0.20 | 0.51 |
| Over 2.77 to 5.16, incl | 0.25 | 0.64 |
| Over 5.16 to 10.16, incl | 0.30 | 0.76 |
| Over 10.16 to 15.24, incl | 0.38 | 0.89 |
| Over 15.24 to 25.40, incl | 0.43 | 1.02 |
| Over 25.40 | 0.51 | 1.14 |

3.3.3.5 Decarburization shall be measured by the microscopic method or by Rockwell Superficial 30-N scale or equivalent hardness testing method on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization or lack of decarburization thereon.

3.3.3.5.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.

3.4 Quality:

3.4.1 Steel shall be premium aircraft-quality conforming to AMS-2300 or MAM-2300. It shall be multiple melted using consumable electrode vacuum process in the remelt cycle.

3.4.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

SAE AMS-6305 Revision B

3.4.2.1 Bars and mechanical tubing ordered hot rolled or cold drawn, or ground, turned, or polished shall, after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.

3.4.3 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

3.5 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars and tubing will be acceptable in mill lengths of 6 - 20 feet (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet (3 m).

3.6 Tolerances: Shall conform to all applicable requirements of the following:

3.6.1 Bars: AMS-2251 or MAM-2251.

3.6.2 Mechanical Tubing: AMS-2253 or MAM-2253.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests: Tests for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing: Shall be in accordance with the following; a lot shall be the consumable electrode remelted ingots produced from steel originally melted as a single furnace charge:

4.3.1 Bars and Mechanical Tubing: AMS-2370.

4.3.2 Forgings and Forging Stock: AMS-2372.

4.3.3 Samples for macrostructure rating (3.3.1) shall be full cross-sectional specimens obtained from the finished billet or suitable rerolled product representing the top and bottom of at least the first, middle, and last usable ingot of each heat.

4.4 Reports: The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition, macrostructure, grain size, and frequency-severity cleanliness rating of each heat. This report shall include the purchase order number, lot number, AMS-6305B, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.