



400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION



AMS 6485G

Issued NOV 1959
Revised JUL 1989
Noncurrent OCT 1991
Reaf. Noncur. OCT 2001

Superseding AMS 6485F

Steel Bars and forgings
5.0Cr - 1.3Mo - 0.5V (0.38 - 0.43C)

UNS T20811

NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of October 1991. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE.

SAENORM.COM: Click to view the full PDF of this document

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2001 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:

(724) 772-7161

FAX: (724) 776-0243

TO PLACE A DOCUMENT ORDER:

(724) 776-4970

FAX: (724) 776-0790

SAE WEB ADDRESS:

<http://www.sae.org>

1. SCOPE:

1.1 Form:

This specification covers an aircraft-quality, low-alloy steel in the form of bars, forgings, and forging stock.

1.2 Application:

Primarily for parts requiring a combination of relatively-high strength, fatigue resistance, toughness, ductility, and thermal stability for operation between -100° and +1000°F (-73° and +538°C) and where such parts may require welding during fabrication.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2251 Tolerances, Low-Alloy Steel Bars
- MAM 2251 Tolerances, Metric, Low-Alloy Steel Bars
- AMS 2259 Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
- AMS 2301 Aircraft Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
- AMS 2310 Qualification Sampling of Steels, Transverse Tensile Properties
- AMS 2350 Standards and Test Methods
- AMS 2370 Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock
- AMS 2372 Quality Assurance Sampling of Carbon and Low-Alloy Steels, Forgings and Forging Stock
- AMS 2375 Control of Forgings Requiring First Article Approval
- AMS 2806 Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
- AMS 2808 Identification, Forgings

2.1.2 Aerospace Standards:

- AS1182 Standard Machining Allowance, Aircraft Quality and Premium Quality Steel Products

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 Mechanical Testing of Steel Products

ASTM E21 Elevated Temperature Tension Tests of Metallic Materials

ASTM E112 Determining Average Grain Size

ASTM E350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingots, Iron, and Wrought Iron

ASTM E381 Macroetch Testing, Inspection, and Rating Steel Products Comprising Bars, Billets, Blooms, and Forgings

2.3 U.S. Government Publications:

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Carbon	0.38	0.43
Manganese	0.20	0.40
Silicon	0.80	1.00
Phosphorus	--	0.020
Sulfur	--	0.020
Chromium	4.75	5.25
Molybdenum	1.20	1.40
Vanadium	0.40	0.60
Nickel	--	0.25
Copper	--	0.35

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition:

The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A 370:

3.2.1 Bars:

3.2.1.1 Bars 0.500 inch (12.70 mm) and Under in Nominal Diameter or Distance Between Parallel Sides: Cold finished having tensile strength not higher than 135,000 psi (931 MPa).

3.2.1.2 Bars Over 0.500 inch (12.70 mm) in Nominal Diameter or Distance Between Parallel Sides: Hot finished and annealed having hardness not higher than 235 HB, or equivalent, except that bars ordered cold finished may have hardness as high as 255 HB, or equivalent.

3.2.2 forgings: As ordered.

3.2.3 Forging Stock: As ordered by the forging manufacturer.

3.3 Properties:

The product shall conform to the following requirements; hardness and room temperature tensile testing shall be performed in accordance with ASTM A 370:

3.3.1 Macrostructure: Visual examination of transverse sections as in 4.3.3 from bars, billets, and forging stock, etched in accordance with ASTM E381, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the following macrographs of ASTM E381:

Section Size		
Square Inches	Square Centimetres	Macrographs
Up to 36, incl	Up to 232, incl	S2 - R1 - C2
Over 36 to 100, incl	Over 232 to 645, incl	S2 - R2 - C3
Over 100	Over 645	As agreed upon

3.3.2 Decarburization:

3.3.2.1 Bars ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.

3.3.2.2 Allowable decarburization of bars and billets ordered for redrawing or forging or to specified microstructural requirements shall be as agreed upon by purchaser and vendor.

3.3.2.3 Decarburization of bars to which 3.3.2.1 or 3.3.2.2 is not applicable shall be not greater than shown in Table I.

TABLE I

Nominal Diameter or Distance Between Parallel Sides Inches	Depth of Decarburization Inch
Up to 0.375, incl	0.010
Over 0.375 to 0.500, incl	0.015
Over 0.500 to 0.625, incl	0.020
Over 0.625 to 1.000, incl	0.025
Over 1.000 to 2.000, incl	0.035
Over 2.000 to 3.000, incl	0.048
Over 3.000 to 4.000, incl	0.062
Over 4.000 to 5.000, incl	0.094
Over 5.000	0.125

TABLE I (SI)

Nominal Diameter or Distance Between Parallel Sides Millimetres	Depth of Decarburization Millimetres
Up to 9.52, incl	0.25
Over 9.52 to 12.70, incl	0.38
Over 12.70 to 15.88, incl	0.51
Over 15.88 to 25.40, incl	0.64
Over 25.40 to 50.80, incl	0.89
Over 50.80 to 76.20, incl	1.22
Over 76.20 to 101.60, incl	1.57
Over 101.60 to 127.00, incl	2.39
Over 127.00	3.18

3.3.2.4 Decarburization shall be measured by the microscopic method or by Rockwell Superficial 30-N scale or equivalent hardness testing method on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization or lack of decarburization thereon.

3.3.2.4.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.

3.3.3 Properties After Heat Treatment: Specimens shall meet the requirements of 3.3.3.1, 3.3.3.2, and 3.3.3.3 after being austenitized by heating to $1850^{\circ}\text{F} \pm 25$ ($1010^{\circ}\text{C} \pm 14$), holding at heat for 15 - 45 minutes, and cooling in air to room temperature and tempered three times by heating to a temperature not lower than 1000°F (538°C), holding at heat for 2 - 3 hours, and cooling in air. Grain size specimens need not be tempered.

3.3.3.1 Tensile Properties:

3.3.3.1.1 Longitudinal: These requirements apply to specimens taken from bars and from forging stock 25 square inches (161 cm^2) and under in cross-sectional area, from forgings with axis approximately parallel to the forging flow lines, and from coupons of forging stock over 25 square inches (161 cm^2) in cross-sectional area forged to 25 square inches (161 cm^2) prior to heat treatment as in 3.3.3. Tests in the longitudinal direction are not required on product tested in the transverse direction.

3.3.3.1.1.1 At Room Temperature:

Tensile Strength, minimum	260,000 psi (1793 MPa)
Yield Strength at 0.2% Offset, minimum	215,000 psi (1482 MPa)
Elongation in 4D, minimum	8%
Reduction of Area, minimum	30%

3.3.3.1.1.2 At 1000°F (538°C): Specimens shall be heated to $1000^{\circ}\text{F} \pm 10$ ($540^{\circ}\text{C} \pm 6$) held at heat for 20 - 30 minutes, and tested in accordance with ASTM E21 at $1000^{\circ}\text{F} \pm 10$ ($538^{\circ}\text{C} \pm 6$).

Tensile Strength, minimum	175,000 psi (1207 MPa)
Yield Strength at 0.2% Offset, minimum	135,000 psi (931 MPa)
Elongation in 4D, minimum	10%
Reduction of Area, minimum	35%

3.3.3.1.2 Transverse: Shall be as follows, determined on specimens, selected and prepared in accordance with AMS 2310, from bars and forging stock over 25 to 256 square inches (161 to 1652 cm²), incl, in cross-sectional area:

Tensile Strength, minimum	260,000 psi (1793 MPa)
Yield Strength at 0.2% Offset, minimum	215,000 psi (1482 MPa)
Reduction of Area	

Section Size		Percent	
Square Inches	Square Centimetres	Minimum	Average
Over 25 to 75, excl	Over 161 to 484, excl	6	15
75 to 100, incl	484 to 645, incl	6	10
Over 100 to 150, incl	Over 645 to 968, incl	5	-
Over 150 to 225, incl	Over 968 to 1452, incl	4	-
Over 225 to 256, incl	Over 1452 to 1652, incl	3	-

3.3.3.2 Hardness: Shall be 50 - 56 HRC, or equivalent, but the product shall not be rejected on the basis of hardness if the tensile property requirements of 3.3.3.1.1.1 or 3.3.3.1.2 are met.

3.3.3.3 Grain Size: Shall be as follows, determined in accordance with ASTM E112:

3.3.3.3.1 Bars and Forgings 2.50 Inches (63.5 mm) and Under in Cross-Sectional Thickness: 7 or finer with occasional grains as large as 5 permissible.

3.3.3.3.2 Bars and Forgings Over 2.50 Inches (63.5 mm) in Cross-Sectional Thickness: 5 or finer with occasional grains as large as 3 permissible.

3.4 Quality:

3.4.1 Steel shall be aircraft-quality conforming to AMS 2301.

3.4.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.4.2.1 Bars ordered ground, turned, or polished shall be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.

3.4.2.2 Product ordered to surface conditions other than ground, turned, or polished shall, after removal of the standard machining allowance, be free from seams, laps, tears, cracks, and other defects exposed to the machined surfaces. Standard machining allowance shall be in accordance with AS 1182.

3.4.2.3 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

3.5 Sizes:

Except when exact lengths or multiples of exact lengths are ordered, straight bars will be acceptable in mill lengths of 6 - 20 feet (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet (3 m).

3.6 Tolerances:

Bars shall conform to all applicable requirements of AMS 2251 or MAM 2251.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.2.1.1 Composition (3.1), macrostructure (3.3.1), and frequency-severity cleanliness rating (3.4.1) of each heat.

4.2.1.2 Condition (3.2.1), decarburization (3.3.2), and tolerances (3.6) of each lot of bars.

4.2.1.3 Room-temperature longitudinal tensile properties (3.3.3.1.1.1), hardness (3.3.3.2), and grain size (3.3.3.3) of each lot of bars, forgings, and forging stock after heat treatment.

4.2.1.4 Room-temperature transverse tensile properties (3.3.3.1.2) of each lot of bars and forging stock after heat treatment.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for tensile properties at 1000°F (538°C) of bars, forgings, and forging stock and grain flow of die forgings (3.4.2.3) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.